

Silver Embedded Textiles: A Novel Barrier to Infectious Diseases

Andrew Duong

Reviewed by: Dr. Uyen Nguyen

Disclaimer: The authors of this report and InfectionControl.tips declare *no conflict* of interest with the following critical evaluation and research. No funds or influence were provided to the authors or InfectionControl.tips by any parties.

Abstract:

Silver is regularly used as an antimicrobial agent in a number of materials. In hospitals, fabric surfaces can be reservoirs for dangerous pathogens. Although regularly cleaning these fabrics would be ideal, it is often not feasible for the already overworked staff. Silver coatings were introduced to assist in reducing the presence of pathogens. In this evaluation, a novel silver-embedded fabric was tested for its bactericidal activity. Preliminary results showed that the silver-embedded fabric sample decreased microbial load by over 99.9% following a 24-hour exposure. This demonstrates that the use of silver-embedded fabrics provides an advantage over untreated textiles in reducing bacterial populations.

Introduction:

In hospitals, textiles represent a consistent, but unavoidable reservoir of microorganisms. Used in bedding, clothing, and as protective covers (among others), patients and healthcare workers are in constant contact with these fabrics. Fabrics are typically used for draping between patient areas and on furniture in hospitals. These areas are especially prone to harbouring dangerous pathogens (Noskin *et al.*, 2000) and antimicrobial resistant microorganisms are increasingly being identified in these fabrics.

Silver has been in use in fabrics for nearly 30 years (Deitch *et al.*, 1987). The antimicrobial properties of silver are

well known and lauded for their relative non-toxicity. Silver coatings are typically applied to fabrics to reduce/eliminate the presence of harmful pathogens (Kleuh *et al.*, 2000). Like many antimicrobial coatings, their antimicrobial effectiveness is optimized with regular cleaning. For most fabrics, this requires laundering at high temperatures. One potential negative outcome of this is that the coating may be worn away with repeated cleaning (Perera *et al.*, 2013).

An alternative to silver-coated fabrics is the use of fabrics where silver is embedded to form a polymer with each of the fibres making up the fabric ([Clinical Fabric Solutions](#)). The fibres

are embedded with silver during the manufacturing process, increasing retention of silver, even after repeated laundering. In this evaluation, the antimicrobial properties of a silver-embedded fabric are examined.

Methods:

All experiments were performed by a third party laboratory.

To evaluate the antimicrobial activity of the fabric, small, square samples (weighing $0.4\text{g} \pm 0.05\text{g}$) of both normal denim and silver-embedded denim were inoculated with 4.43×10^5 colony forming units (CFU) of *Escherichia coli* (ATCC 25922) suspended in 10 ml of 0.2% TSB supplemented with 0.05% Triton X-100. After 24 h incubation at 37°C , the samples were neutralized by adding 10 ml of Dey/Engley Neutralizing Broth (1x) directly to the sample. The samples were vortexed vigorously for 1 min to effectively disperse all microorganisms from the sample surface, serially diluted 1:10 in TSB, and plated on tryptic soy agar to isolate between 25–250 colonies per plate. Tryptic soy agar plates were incubated overnight at 37°C and counted. As an additional control, a sample of the

inoculum was incubated and treated in parallel without the fabric samples to control for any effect that the normal denim may have on the assay.

Results:

Following 24 h incubation of the culture without any additional fabric added, the sample continued to grow, reaching a total microbial load of 1.95×10^6 CFU. In the non-treated sample, there was a modest increase in the microbial load, increasing from 4.43×10^5 CFU to 6.35×10^5 CFU (Table 1). In the treated samples, the average microbial load was reduced to 2.49×10^2 CFU (~3.48 log reduction).

Discussion:

Fabric and other textiles are employed in a variety of environments and can harbour pathogens. Especially prevalent in healthcare environments such as hospitals and nursing homes, cleaning of these textiles is critical for limiting the spread of pathogens. In this evaluation, the use of silver-embedded denim resulted in a 99.95% reduction in bacterial load (3.48-fold log reduction) following a 24 hour incubation in nutrient

Table 1: Microbial load following 24 h incubation with fabric sample

Sample	Starting Inoculum	Number of Microorganisms Recovered	Logarithmic Reduction
Control	4.43×10^5 CFU	1.95×10^6 CFU	N/A
Untreated Denim	4.43×10^5 CFU	6.35×10^5 CFU	N/A
Ag ²⁺ Denim (#1)	4.43×10^5 CFU	4.90×10^1 CFU	3.96
Ag ²⁺ Denim (#2)	4.43×10^5 CFU	4.50×10^2 CFU	2.99

broth. In contrast, there was no reduction in CFU with using traditional denim. This suggests that silver-embedded textiles can be a beneficial alternative to traditional textiles in hospitals and other public areas prone to transfer of infectious diseases.

Both control samples (without added fabric and with untreated denim) demonstrated an increase in the number of CFU. Within the 24-h period, there was a 4.4-fold increase the number of *E. coli*, whereas the untreated denim showed a 1.4-fold increase. Although the presence of denim did not have any antimicrobial effect, it is possible that the untreated denim may have limited bacteriostatic antimicrobial activity. Denim has not been previously identified as a material with antimicrobial properties (Chun *et al.*, 2009).

The silver-embedded textiles showed a remarkable reduction in microbial load following a 24-h incubation. The nearly 3.5-fold log reduction represents >99.9% reduction of *E. coli* in the sample. This suggests that similar to other silver-based technologies, silver in the denim has bactericidal effects (Agnihotri *et al.*, 2013; Schwartz *et al.*, 2014). However, further testing to evaluate its effectiveness in a clinical environment should be performed to determine if these results can be directly translated.

There is a unique advantage in the use of silver-embedded textiles compared to silver-coated textiles. After repeated

washes, silver nanoparticles and the coating are released in miniscule amounts (Perera *et al.*, 2013; Lombi *et al.*, 2014). The antimicrobial efficacy of these fabrics following repeated washes has not been evaluated based on our literature search. It has been hypothesized that repeated washes will reduce its antimicrobial properties. However, this hypothesis is currently not substantiated.

One limitation of this experiment is the lack of silver-coated fabrics as a control. Evaluation of silver-embedded fabrics in parallel with silver-coated fabrics would show if one is more appropriate for use in healthcare systems than the other. In addition, testing of the materials after repeated washes could provide insight into the cost-effectiveness of one textile over another.

Conclusion:

Silver-embedded denim is highly effective in reducing the number of bacteria after a 24-h period. The bactericidal properties of the silver eliminated over 99.9% of the bacteria, suggesting a potential clinical use of silver-embedded denim. Additional testing is required to evaluate if these findings can be translated to clinical use. These preliminary results suggest that this technology has the potential to greatly reduce bioburden populations in textiles and improve patient outcomes following hospital stays.

References:

1. Agnihotri S, Mukherji S, Mukherji S. Immobilized silver nanoparticles enhance contact killing and show highest efficacy: elucidation of the mechanism of bactericidal action of silver. *Nanoscale*. 2013;5(16):7328-40.
2. Chun DT, Foulk JA, McAlister DD. Testing for antibacterial properties of cotton/flax denim. *Industrial Crops and Products*. 2009 Mar 31;29(2):371-6.
3. Deitch EA, Marino AA, Malakanok V, Albright JA. Silver nylon cloth: in vitro and in vivo evaluation of antimicrobial activity. *The Journal of Trauma*. 1987 Mar;27(3):301-4.
4. Klueh U, Wagner V, Kelly S, Johnson A, Bryers JD. Efficacy of silver-coated fabric to prevent bacterial colonization and subsequent device-based biofilm formation. *Journal of Biomedical Materials Research*. 2000 Jan 1;53(6):621-31.
5. Lombi E, Donner E, Scheckel KG, Sekine R, Lorenz C, Von Goetz N, Nowack B. Silver speciation and release in commercial antimicrobial textiles as influenced by washing. *Chemosphere*. 2014 Sep 30;111:352-8.
6. Noskin GA, Bednarz P, Suriano T, Reiner S, Peterson LR. Persistent contamination of fabric-covered furniture by vancomycin-resistant enterococci: implications for upholstery selection in hospitals. *American Journal of Infection Control*. 2000 Aug 31;28(4):311-3.
7. Perera S, Bhushan B, Bandara R, Rajapakse G, Rajapakse S, Bandara C. Morphological, antimicrobial, durability, and physical properties of untreated and treated textiles using silver-nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2013 Sep 5;436:975-89.
8. Schwartz J, Goss S, Facchin F, Manizate F, Gendics C, Braitman E, Lantis J. A prospective two-armed trial assessing the efficacy and performance of a silver dressing used postoperatively on high-risk, clean surgical wounds. *Ostomy Wound Manage*. 2014 Apr 1;60:30.